

<b>Thickness:</b> TBD	<b>Grade:</b> Industrial - SX
-----------------------	-------------------------------

<b>Technical Data</b>
-----------------------

Physical Property	Test Standard	Metric	Standard	Tolerance
Finished Thickness	ANSI 208.2	TBD	TBD	+/- 0.125 mm
Density	EN 323	720 Kg/m3	45.0 lb/ft3	+/- 16 Kg/m3
Internal Bond	EN 319	0.58 N/mm2	85 psi	n/a
Modulus of Rupture	EN 310	11.4 N/mm2	1650 psi	n/a
Modulus of Elasticity	EN 310	2293 N/mm2	332,600 psi	n/a
Screw Holding - Face	EN 320	1059 N	238 lb	n/a
Screw Holding - Edge	EN 320	734 N	165 lb	n/a
Residual Moisture Content	EN 322	7%	7%	+/- 1.0 %
Residual Formaldehyde Content	ANSI 208.2	≤ 0.06 ppm	≤ 0.06 ppm	n/a
Squareness	ANSI 208.2	1.0 mm/m	.012 in.ft	n/a
Finished Length	ANSI 208.2	+/- 1.6 mm	+/- 0.063 in	n/a
Finished Width	ANSI 208.2	+/- 1.6 mm	+/- 0.063 in	n/a
Sanding Finish [Grit]	n/a	120	120	n/a

**Notes:**

1. Recommended specifications pending customer approval.
2. Formaldehyde Emissions are governed by EPA TSCA Title VI Regulations.